



**DIVERSIFIED**  
TESTING LABORATORIES, INC.  
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET  
P.O. BOX 4004  
BURLINGTON, NORTH CAROLINA 27215  
PHONE (336) 227-7710 • FAX (336) 227-1175  
www.diversifiedtestinglabs.com

November 27, 2018

Ms. Ann Sawchak  
EXPAND SYSTEMS, LLC  
771 Shallowford Road, Suite 102  
Kennesaw, GA 30144

Reference: Laboratory Test Report  
Lab Identification No. 33264  
Invoice No. 64429

Dear Ms. Sawchak:

One (1) fabric sample, identified as **2452 CHENILLE**, was received and tested in accordance with the National Fire Protection Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2015 Edition, (Test 1)". The results are as follows:

<u>Specimen Number</u>	<u>Test Results</u> <u>Residual Flame</u> (seconds)	<u>Weight Loss</u> (percent)
1	0.0	4.15
2	0.0	0.89
3	0.0	1.96
4	0.0	0.82
5	0.0	9.26
6	0.0	18.46
7	0.0	10.44
8	0.0	2.34
9	0.0	3.05
<u>10</u>	<u>0.0</u>	<u>2.35</u>
AVG	0.0	5.37

The sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr

