



DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

March 6, 2018

Ms. Ann Sawchak
EXPAND SYSTEMS, LLC
771 Shallowford Road, Suite 102
Kennesaw, GA 30144

Reference: Laboratory Test Report
Lab Identification No. 29543
Invoice No. 60693

Dear Ms. Sawchak:

One (1) fabric sample, identified as **5196 – LEENANE – PRETREATED**, was received and tested in accordance with the California Technical Bulletin 117-2013, Section 1, Cover Fabric Test. The results are as follows:

Test Results
Vertical Char Lengths

18mm

22mm

19mm

The sample submitted **meets** the requirements of the above standard. There were no ignitions or smoldering after 45 minutes on any of the three specimens tested. In addition, none of the three test specimens displayed a char which was greater than 45 mm.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr

